
Plastic body No. 24, individually wrapped

Chemical analysis:

SiO ₂	65,8 %
Al ₂ O ₃	23,1 %
TiO ₂	1,3 %
Fe ₂ O ₃	0,9 %
CaO	2,8 %
MgO	1,3 %
K ₂ O	4,0 %
Na ₂ O	0,8 %

Ceramic data:

Dry shrinkage in %:

7

Firing temperature:

1070 °C

1140 °C

Firing colour:

white

light

Firing shrinkage in %:

4

6

Water absorption in %:

6

1

Coefficient of thermal expansion (CTE):

20 °C - 400 °C

75

20 °C - 500 °C

78

20 °C - 600 °C

89

CTE * 10⁻⁷/K